





MasterSeal Roof 2111


Spray applied crack-bridging waterproofing roof system based on MasterSeal M 811

Consumption

(approx):

	Primer	According to substrate. See technical data sheet MasterSeal M 811 or consult technical service	
	Membrane (spray applied)	MasterSeal M 811 Highly reactive, 2-component spray applied polyurea hybrid waterproofing membrane, mixing ratio 1:1 by volume.	min. 2.3 kg/m ²
	Top coat 1 layer	MasterSeal TC 269 Pigmented, 2 C PU, high solid, elastic, UV- and weather resistant, silk glossy	1 x 0.15-0.20 kg/m ²
	Top coat (alternative)	MasterSeal TC 681 pigmented, polyaspartic, 2-component, fast curing, low solvent content, UV- and weather resistant,	1 x 0.18-0.23 kg/m ²

Note: Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.




MasterSeal Roof 2111

Spray applied crack-bridging waterproofing roof system based on MasterSeal M 811

CE-MARKING EN 1504-2

CE	
1119	
Master Builders Solutions Deutschland GmbH Donnerschweer Str. 372, D-26123 Oldenburg	
15	
211101	
EN 1504-2:2004	
Surface protection product - coatings EN 1504-2: ZA.1d, ZA.1e, ZA.1f and ZA.1g	
Abrasion resistance	NPD
Permeability to CO ₂	Sd > 50
Permeability to water vapour	Class I
Capillary absorption and permeability to water	< 0.01 kg/(m ² xh ^{0,5})
Thermal compatibility	≥ 1.5 N/mm ²
Resistance to severe chemical attack	Reduction of hardness < 50 %
Crack bridging ability	Dynamic: B4: (23 °C) Static: A5: (23 °C)
Impact resistance	Class III
Adhesion strength by pull-off test	≥ 1.5 N/mm ²
Reaction to fire	Cfl-s1 Broof-T2
Artificial aging	OK
Skid resistance	NPD

NPD = No performance determined



MasterSeal Roof 2111

Spray applied crack-bridging waterproofing roof system based on MasterSeal M 811

DISCLAIMER

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical helpline for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer. All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.

Master Builders Solutions Deutschland GmbH
Donnerschweer Straße 372
26123 Oldenburg
Germany

System build-up MasterSeal Roof 2111 – January 21
Version 01